

CPIC BRASIL Fibras de Vidro Ltda.

Rodovia Campinas - Tietê SP 101, km 40,5 Cx. Postal 1890 - Capivari - SP - CEP 13368-001 Tel.: +55 19 3492 9000 SAC: 0800 055 4112 www.cpicfiber.com.br

Technical Data Sheet Chopped Strands 301HP

Reinforcement for Polyamide Resins

Product Description

Chopped Strand 301HP is made from continuous filaments of E-boron free glass, which receives a sizing specially designed for the reinforcement of Polyamide.

The 301HP sizing has an outstanding resistance to hydrolysis and good glycol

Product Application

resistance.

The Chopped Strands 301HP is designed for the production of grainy thermoplastics extrusion reinforced, used in the production of injection molding pieces



Product Benefits

- · Easy dispersion in the extruder, low torque absorbed
- · Excellent dry flow characteristics
- · Outstanding strand integrity
- Low fines
- · Excellent mechanical properties
- No loss of mechanical performance in formulation with stearates

Identification

Example: ECS301HP-4,5-H Chopped Strands

301HP: CPIC BRAZIL sizing reference **4,5:** Nominal fiber length (mm)

H: Filament Diameter

n: Filament Diamete



CPIC BRASIL Fibras de Vidro Ltda.

Rodovia Campinas - Tietê SP 101, km 40,5 Cx. Postal 1890 - Capivari - SP - CEP 13368-001 Tel.: +55 19 3492 9000 SAC: 0800 055 4112 www.cpicfiber.com.br

Technical Characteristics

Length		Filament Diameter (µm)		Loss on Ignition (%)	Moisture (%)
mm	in	μm		ISO 1887	ISO 3344
3,0	1/8	10 ±1 (H)	14 ±1 (L)	0,45 ± 0,10	≤ 0,05
4,5	3/16	10 ±1 (H)	14 ±1 (L)	0,45 ± 0,10	≤ 0,05

Packaging

Available packaging for Chopped Strands 301HP are presented below.

Packaging	Bags per pallet	Pallet Dimension L x W x H (mm)	Net Weight (Kg)
Polyethylene bags	28	1140 x 1140 x 920	700
Polyethylene bags	44	1140 x 1140 x 1180	1100
Big Bag	01	1140 x 1140 x 1200	1000

The packaging unit is the pallet. For big bag packaging stacking is not recommended.

Storage

The Chopped Strands 301HP should be stored away from heat and moisture, and in their original packaging. The best conditions are temperatures between 15 and 35°C and humidity between 35 and 65%. If the product is not stored under these specifications, it is advisable to condition it in the workshop for at least 24 hours before use, to prevent condensation.

CPIC Brazil recommends that the material be used according to FIFO method (first in, first out).



Integrated Management System Certifications:

ISO9001

ISO14001

ISO45001